

## PLANT PROTECTION DEVICE

The invention relates to a plant protection device to be used especially for the nursery garden trade, particularly for vine, fruit trees, ornamental trees and for  
5 forestry.

In the field of wine growing, the young plants are products of high added-value for the nursery farmers and the wine growers. In 90 % of the cases, the trees are planted without roots, directly to open ground and they have to be protected  
10 against bad weather conditions for one to two years to restart the growing in good conditions.

In the field of fruit growing, the farmers confront a growing population of rodents such as rabbits, hares, and field-mice etc., which are able to cause extensive  
15 damage by destroying up to 100 % of a patch. In practice, in order to fight these rodents, it is necessary to protect especially the stem and the roots during a period of 2 – 3 years.

In the rest of this text, the term “plants” denotes young sprouts cultivated in horticultural, viticultural or arboreal nurseries, as well as young trees or older  
20 trees, the growth of which in terms of roots and leaves remains weak, in practice in the order of 50 – 120 cm.

To protect the plants during their growth from pests, especially from rodents, but  
25 also to an extent from the attacks of insects and fungi as well as the spread of weed, several types of solutions have at present been used.

The first solution is spraying phytosanitary products on the plant or to the close vicinity thereof. The main inconvenience is that these phytosanitary products  
30 are, mostly, noxious and consequently considered as polluting agents. This is why the health authorities take at the moment measures aiming to limit the use of this type of products.

A second alternative solution is to protect the plant mechanically by means of plastic tubes or pots, which are totally or partially buried in the soil. Even if these devices fulfil efficiently their plant protection function, we are, however, confronted with a certain number of inconveniences. First of all, the UV radiation (photolysis) weakens the mechanical characteristics of the tube, which finally breaks, and thus does not fulfil anymore the protection function. Moreover, as the tube is not transparent it considerably slows down the photosynthesis process. Further and moreover, these plastic materials are not biodegradable. Consequently, the farmer has two choices. He can take the tubes out of the ground, but this operation will cause a considerable extra cost. Consequently, and most of the time, the tubes remain in the soil, which leads to accumulation of these residues, again as pollutants, which have a direct impact on the environment.

Document FR-A-1468313 describes small bags or pouch packets for protecting fruits directly in the tree. In practice, bags or pouches are made of parchmented paper and have the disadvantage of not being transparent enough to sun beams.

The problem that the invention thus proposes to solve is how to develop means for protecting the plants, which fulfil the following objectives:

- 100 % biodegradability
- mechanical resistance adapted to repeated sprinkling or rain
- mechanical resistance to UV radiation
- wind resistance
- sufficient translucence to assure the photosynthesis
- limited cost.

It came as a surprise to the applicant that parchmentizing or vulcanizing treatments enhance the mechanical properties of tubes made from annual plant

fibres instead of traditional paper fibres by modifying the optical properties, such as decreasing opacity and increasing transparency.

5 The vulcanizing and parchmentizing operations are well known by those skilled in the art and will thus not be described here in more detail.

10 The main point is that the parchmentizing and vulcanizing are operations consisting in treating a fibrous support by immersion, in sulfuric acid (parchmentizing) or in zinc chloride (vulcanizing). This immersion has the effect of forming a cellulose gel to the surface of the fibrous support, giving it after neutralizing, washing and drying, improved greaseproofing, waterproofing, translucence and mechanical resistance characteristics.

15 Consequently, the invention relates to a plant protection device, which is characterized in that it is a tube consisting at least of one parchmentized or vulcanized fibrous support in the form of a sheet containing annual fibres, the device being biodegradable.

20 According to a first characteristic of the invention, the fibrous support to be parchmentized or vulcanized contains at least 20 % by weight of annual fibres, advantageously at least 50 %, preferably 75 % by weight of annual fibres. In practice, the annual plant fibres are fibres such as cotton, ramie, jute, flax, sisal hemp, abaca, kenaf etc.

25 Naturally, the fibrous support may contain other fibres such as unbleached or bleached vegetable fibres obtained from coniferous or deciduous plants; and synthetic fibres such as e.g. viscose, polyvinyl alcohol, these fibres being biodegradable and can be used by themselves or as a mixture, the support being able to non-exclusively comprise additives such as foodstuff colour, carbon black. In practice, the mass of the parchmentized or vulcanized support  
30 is between 50 g/m<sup>2</sup> and 250 g/m<sup>2</sup>, advantageously 100 g/m<sup>2</sup>.

However, the fibrous support can consist exclusively of traditional paper-making fibres e.g. of eucalyptus fibres, and this according to the desired mechanical characteristics.

- 5 As already said, the parchmented or vulcanized fibrous support making up the protection device has a grammage of between 50 and 250 g/m<sup>2</sup>, advantageously 100 g/m<sup>2</sup>, these values corresponding to the grammage of the unitary sheet. In fact, in certain embodiments mentioned in the rest of the description, the device comprises several parchmented or vulcanized sheets  
10 or supports.

- In practice, the protection device is totally or partially buried in the soil. When a part of the device is out of the soil, e.g. for protecting the young plant against weather conditions, especially against the wind, the device has to be sufficiently  
15 transparent for allowing the photosynthesis.

Consequently, and according to another characteristic, the tubular device of the invention has a transparency of 15 % - 25 %, advantageously of 20 %.

- 20 To expel flying insects and to provide the fibrous support with fungicidal, fungistatic or bactericidal properties, the vulcanized or parchmented support is advantageously covered with fungicidal, fungistatic or bactericidal repellent products, preferably non-toxic products, especially essential oils (geraniol, thyme essence, thymol etc.) sprayed to the surface of the support.

25

The protection device can be produced in different forms according to its use.

- When young sprouts are to be protected, the leaves of which have a small diameter, in practice less than 50 cm, the device has, according to a first  
30 embodiment, the form of a core, or sleeve, obtained by rolling spirally the parchmented or vulcanized fibrous support.

The manufacturing technique of cores is perfectly known by an person skilled in the art and will not be described here in more detail. It mainly consists in winding spirally, around a metal tube, a first sheet transferred by a belt by friction on the fixed metal tube. Then, on the first sheet a second sheet is wound and so on, until the desired number has been reached, the lower face of each sheet being coated with adhesive to ensure the cohesion of the assembly. Moreover and in practice, each sheet is wound so that the spirals formed of the same sheet are not superposed.

10 According to the desired rigidity, the core is more or less thick, nevertheless respecting at the same time the transparency characteristics such as those described above.

In this way and according to a first embodiment, the core produced by superposing 2 – 15, advantageously 5, parchmented or vulcanized sheets allowing obtaining an especially rigid product, the lower face of each sheet being covered with adhesive.

In practice, the final product has a mass of between 230 g/m<sup>2</sup> and 1500 g/m<sup>2</sup>, preferably of 500 g/m<sup>2</sup>.

The diameter of the core varies, of course, according to the diameter of the plant to be protected. According to a characteristic of the invention, the rigid cores such as those described above, have a diameter of at least 120 mm, advantageously 360 mm, and even up to 480 mm.

According to a second embodiment, the core is supple in order to allow the storage thereof by laterally crushing the core. In this case, instead of 2 – 15 parchmented or vulcanized sheets, 2 – 5 sheets, advantageously 3 sheets, are provided. In practice, this type of core has a grammage of between 300 and 400 g/m<sup>2</sup>, advantageously of between 350 and 360 g/m<sup>2</sup>.

To guarantee the complete biodegradability of the device of the invention, the adhesive used to guarantee the adhesion of the sheets to each other consists exclusively of biodegradable polymers chosen from the group comprising polyvinyl alcohol, natural rubber, starch, gelatine, polysaccharides, arabic gum, alginate and carboxymethyl cellulose.

In an advantageous embodiment, the adhesive further contains a repellent agent, e.g. an essential oil intended to expel insects and rodents, and possibly fungicidal and bactericidal products. In fact, the repellent agent and the fungicidal and bactericidal products represent 0.5 % to 20 % by weight of the adhesive, and preferably 5 %.

When the device is used more specifically to protect taller trees, the dimensions and flexibility of the above-described cores are not applicable.

Consequently and in another embodiment, the fibrous support making up the protection device of the invention is of corrugated board type and has the form of a folding corrugated sheet, the dimensions of which vary according to the diameter and the height of the plant to be protected.

In an advantageous embodiment, the corrugated parchmentized and/or vulcanized sheet is glued between two parchmentized and/or vulcaniced sheets. In this case, the adhesive is also biodegradable like the adhesive described above.

To facilitate the bending into a tube form, the sheet is provided with grooves.

In the preceding embodiments, the device according to the invention is constituted of an individual core the dimensions of which are adapted according to the plant to be protected. When the device is used for the protection of small trees, the use is facilitated by making a cut along the entire length thereof. After that, the tube is positioned facing the stem, the free ends of the tube are spread

open, the stem is surrounded, and the tube ends are released around the stem. In this case, it is not practical to place the tube in position by lowering it down from the top of the tree.

5 In an advantageous embodiment, taking into consideration the possible growth of the stem of the tree, the device according to the invention is formed of at least two concentric tubes, having a cut extending throughout the entire length, in practice linearly. When placing in position, the concentric tubes are placed in position the same way as described earlier, in other words facing the stem, so  
10 that the cuts are opposite one another. Then the free ends are spread open, placed around the stem and the free ends bend to surround the tree. Finally, to allow the increase in the diameter of the tube in relation to the growth of the tree size, the concentric tubes roll on top of each other so that the cuts are not opposite one another.

15

Regardless of the number of tubes, it is also possible, in view of the growth of the tree, to make a pre-cut on a part or the entire length of the tube.

In a further embodiment, the device of the invention is a pot allowing, besides  
20 the protection, of course transportation of young sprouts.

In practice, the pot is a core such as described above, one end of which is folded inwards to form a bottom. Of course, the core will consist of several sheets according to the desired rigidity of the pot.

25

The invention also relates to a plant protection process consisting in positioning the above-described device around the plant.

Finally, the object of the invention is a tube made of a parchmented or  
30 vulcanized fibrous support in the form of a sheet.

The invention and the advantages which originate therefrom will become more apparent from the following illustrative examples.

### 1. Rigid core

5

#### ***Manufacturing of the core***

Cores are made on a core manufacturing machine from 10 reels of parchmented paper having a width of 205 mm, referred to as Sulfax white, of 100 g/m<sup>2</sup>, consisting 80 % of eucalyptus and 20 % of flax fibres.

10

These sheets are glued to each other with biodegradable adhesive consisting 70 % of polyvinyl alcohol and 30 % of natural latex.

0.2 % of geraniol, 0.1 % of thyme essence (repulsive agent) and 0.7 % of bone oil, the trade name of which is "Decamp", is introduced into this adhesive.

15

This mixture forms a repulsive agent against rabbits, hares and cervidae.

#### ***Characteristics of the core***

20 The final product of 1225 g/m<sup>2</sup> is composed of:

- 1000 g/m<sup>2</sup> of parchmented paper
- 225 g/m<sup>2</sup> of dry adhesive.

25

Brightness:	-R457	70.0 %
	-CIE	61.2 %
Opacity:		94.5 %
Transparency		16.0 %

30

The thickness of the core is 6 mm, the diameter 360 mm and the height 1.20 m.

The obtained product is rigid and forms an efficient protection for bushes against cervidae and rodents.



## 2. Flexible core

### *Manufacturing of the core*

- 5 Cores are made on a core manufacturing machine from 3 reels of parchmentized paper (reference Sulfax) of  $100 \text{ g/m}^2$ , the width of which is 205 mm, consisting 80 % of eucalyptus and 20 % of flax fibres, .

- 10 These sheets are glued to each other with a biodegradable adhesive composed of 70 % of polyvinyl alcohol and 30 % of natural latex.

0.2 % of geraniol, 0.1 % of thyme essence (repulsive) and 0.7 % of bone oil, the trade name of which is "Decamp", is introduced to this adhesive.

- 15 After being cut to the desired length, the obtained core is then crushed in its diameter between two metal rolls to obtain a flat sleeve, which can be easily stored flat in cardboard boxes or strapped pallets. When in use, the sleeve is brought back into its cylindrical form by pressing the sides inwards at the two folding lines of the sleeve.

20

### *Characteristics of the core*

The final product of  $350 \text{ g/m}^2$  is composed of:

- $300 \text{ g/m}^2$  of parchmentized paper
- $50 \text{ g/m}^2$  of dry adhesive.

25

The thickness of the core is 0.8 mm, the diameter 140 mm and the length 0.60m.

30

Brightness:	-R457	72.6 %
	-CIE	62.1 %
Opacity:		87.5 %
Transparency		25.8 %

Then the obtained product is reset to its cylindrical form so that it can be placed lightly over the plants (coniferous plants, fruit trees) to assure the protection thereof against rodents.

5

### 3. Corrugated sheet

#### ***Manufacturing process***

Corrugated paper composed of microflute, the thickness of which is 1 mm, of  
10 parchmentized paper of 100 g/m<sup>2</sup> and of two coatings of parchmentized paper of 100 g/m<sup>2</sup>, is manufactured on a suitable machine.

The adhesion of the coatings on the microflute is made with an adhesive, the composition of which is similar to the one described in the example 1.

15

The corrugated parchmentized paper sheets are then cut and provided with grooves for allowing adapting this product to the protection of plants.

At the two ends of the paper, fastening means are provided in the form of a tab  
20 allowing maintaining the material in its place. The plant is wrapped up easily and especially without causing injuries to the trunk, the leaves or the roots.

#### ***Characteristics***

The final product has an m<sup>2</sup>-mass of 315 g/m<sup>2</sup>, composed of  
25 - 300 g/m<sup>2</sup> of parchmentized paper  
- 15 g/m<sup>2</sup> of dry adhesive.

	Brightness:	-R457	73.8 %
		-CIE	62.8 %
30	Opacity:		87.6 %
	Transparency		27.5 %

#### 4. Pot

##### ***Manufacturing process***

5 Cores are made on a core manufacturing machine from 4 reels of parchmented paper, the width of which is 205 mm, referenced Sulfax white, of 100 g/m<sup>2</sup>, composed 80 % of eucalyptus and 20 % of flax fibres.

##### ***Mechanical characteristics***

The final product has a mass of 440 g/m<sup>2</sup>, composed of  
10 - 400 g/m<sup>2</sup> of parchmented paper  
- 40 g/m<sup>2</sup> of dry adhesive.

The thickness of the pot is 1.2 mm and the diameter 6 cm. The bottom of the pot is closed by folding inwards one of the ends of the core.

15

##### ***Optical characteristics***

Brightness:	-R457	70.6 %
	-CIE	61.4 %
Opacity:		89.9 %
20 Transparency		22 %

##### ***Uses***

The pot thus created will have two functions:

- 25 1. to serve as a cultivation pot from seeds; thus it can be used in nurseries,
2. owing to its biodegradable properties, the pot can be placed directly to the ground without disturbing the growth of the plant.